

Rheological Additive

Organically Modified Hectorite in Powder Form for Water-Borne Systems

GENERAL INFORMATION

BENAQUA 4000 rheological additive is an easily dispersible powder designed for lower-gloss and matt latex paints, textured and high-build coatings and water-borne adhesives. It is especially useful in systems that are diluted with water prior to use.

BENAQUA 4000 provides high viscosity in the low-to medium-shear-rate region. It gives superior sag resistance at low package viscosity compared with conventional thickeners, as well as improved shear-thinning rheology. Textured and stippled effects are enhanced and paints exhibit a richer appearance.

PHYSICAL PROPERTIES

Composition	polymer modified clay
Color / Form	off-white, finely divided powder
Density	1,63 g/cm ³
Non-volatile content	100%

APPLICATIONS

Adhesives

- Ready mixed
- Powder

Mastics and sealants**Paints**

- Dry-fall paints
- High-build paints
- Matt latices
- Plasterboard coatings
- Primers/sealers
- Roads marking paints
- Semi-gloss latices
- Textured paints

KEY PROPERTIES

BENAQUA 4000 rheological additive

rheological properties

- good mid-shear-rate viscosity
- excellent shear-thinning
- excellent suspension

application performance

- efficient spray atomisation
- enhanced textured and stippling effects (roller or spray applied)
- minimised mud cracking
- superior sag resistance

paint stability

- good storage stability at elevated temperature
- good freeze/thaw stability
- enzyme resistance
- colorant addition stability

easy to use

- easily incorporated in the mill-base and letdown stages or as aqueous pre-gel

INCORPORATION

BENAQUA 4000 additive can be added via a choice of methods, depending on the equipment available and the formulation type. It is not shear sensitive and is easily incorporated directly in the mill-base or via a pre-gel before the letdown stages. The key to developing optimum performance is to achieve good wetting and hydration. Optimum mixing conditions are obtainable with a toothed blade disperser (e.g. Cowles) run at high peripheral speeds, or rotor stator mixers.

Because BENAQUA 4000 is partially associative, its full thickening efficiency may not be realised until the resin is added to the system. pH adjustment of the batch to pH 8.5–10.0 will enhance performance.

NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.

© Copyright 2006, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

Mill-base Addition

BENAQUA 4000 is added to water (pH 8.5–10.0) and mixed at moderate speed until a smooth dispersion is formed (5–10 min.). The remaining ingredients are added and dispersed under high shear. The letdown stage is completed and the batch adjusted to pH 8.8–10.0.

1. Water
2. pH to > 8.5 **
3. BENAQUA 4000
mix under medium shear
4. glycols
5. dispersants
6. defoamers
7. biocides
8. pigments/extenders
disperse
9. letdown
adjust pH to 8.5–10.0

Alternatively, BENAQUA 4000 can be added as the last ingredient in the mill-base and dispersed for 15 min. This results in improved pigment wetting, shortened dispersion times and minimum foam development.

** The pH adjustment point will depend on the type of formulation used:

- low pH binders and/or lower-PVC (<50%) systems – adjust pH of the dispersion water
- neutral-alkaline binders and/or higher-PVC (>50%) systems, or where the water for dispersion is limited – adjust pH after letdown

Post Mill-base Addition

1. mill-base (dispersed)
2. water (if required)
3. BENAQUA 4000
thoroughly disperse
4. latex resin
5. water
mix at low speed
adjust to pH 8.5–10.0

Pre-gel Method

1. water
2. preservative (non-alkaline)
3. BENAQUA 4000
disperse under optimal conditions for 10–15 minutes
adjust to pH 8.5–10.0 in the final paint

LEVELS OF USE

The typical levels of use for BENAQUA 4000 are 0.3% to 2.0% by weight.

HANDLING AND SAFETY

More detailed information on handling and safety for each product is included in the relevant material safety data sheet, available for each product.

STORAGE RECOMMENDATIONS

Store in a cool, dry location.

PACKAGING

BENAQUA 4000 rheological additive is available in multi-ply paper bags. Please contact your local Elementis Specialties representative for the packaging available in your region.

SHELF LIFE

BENAQUA 4000 has a shelf life of 2 (two) years from date of manufacture.

PRODUCT NUMBER

10845

QUALITY ASSURANCE

Since 1992 the company is a holder of the ISO 9001 / ISO 9002 certificates, which guarantees that all operations are conducted according to the stipulated standards.

USA Head Office

Elementis Specialties, Inc.
P.O. Box 700
329 Wyckoffs Mill Road
Hightstown, NJ 08520 USA
Tel.: +1 609 443 2500
Fax: +1 609 443 2422

Europe

Elementis Service Centre NV
De Kleetlaan 12A, P.O. Box 3
1931 Diegem, Belgium
Tel.: +32 2 790 76 00
Fax: +32 2 790 76 60

Asia

Elementis Specialties, Inc.
120 Jalan Kapar 27/89
40400 Shah Alam
Malaysia
Tel.: +60 3 5192 2887
Fax: +60 3 5192 3887

Japan

Elementis Japan KK
15-14 Minaminisemba 1-Chome
Chou-Ku, Osaka
542-0081 Japan
Tel.: +81 6 6267 6211
Fax: +81 6 6267 6215