

Rheological Additive for Non-Polar to Medium-Polarity Aliphatic and other Solvent Systems - Very Easily Dispersible

GENERAL INFORMATION

BENTONE SD-1 rheological additive is an organic derivative of a bentonite clay. It is a very easily dispersible additive for systems containing primarily aliphatic and other non-polar to medium-polarity solvents. BENTONE SD-1 can be added at any point in the paint manufacturing process and can be used for post-correction.

It provides viscosity increase, reduces sagging of coatings on vertical surfaces and prevents settling of pigments and fillers.

PHYSICAL PROPERTIES

Composition	organic derivative of a bentonite clay
Color / Form	very light cream, finely divided powder
Density	1.47 g/cm ³

APPLICATIONS

Coating systems containing common aliphatic solvents e. g.:

- Anti-corrosive paints
- Bituminous coatings
- Decorative alkyd paints
- Do-it-yourself paints
- Printing inks
- Primers, fillers, undercoats
- Traffic paints
- Wood stains

KEY PROPERTIES

BENTONE SD-1 rheological additive

- is a cost-effective replacement for conventional organoclay additives
- disperses very easily, even under low shear conditions

- provides stable viscosity build, controls sag and pigment settling
- eliminates the need for pregels
- needs no chemical activator
- can be added as a powder to the millbase either before or after the pigment dispersion or during letdown

INCORPORATION

BENTONE SD-1 additive is a readily dispersible organoclay for non-polar to medium-polarity organic applications. Incorporation at any point in the manufacturing process is possible using all normal paint-making equipment. This rheological additive can be incorporated in the pigment grind under high shear and under low shear in the letdown tank. A chemical activator is not required to disperse BENTONE SD-1 in conventional solvent containing paints.

BENTONE SD-1 can be incorporated in the pigment grind under high shear without sensitivity to overshear.

BENTONE SD-1 can also be incorporated under mixing rather than grinding conditions. Its dispersion does, however, require some minimal shear (minimum tip speed 4 m/s when a dissolver is used). The paint to which it is to be added should have good movement in the letdown tank as BENTONE SD-1 additive is sifted in. Sufficient time for full activation should be allowed. The amount of time required will depend upon the size and configuration of the tank, the type and speed of agitator in use and the viscosity and solids of the system.

BENTONE SD-1 does not disperse efficiently at low shear in cold systems (the same holds true for conventional organoclays)

The best rheological performance under letdown conditions is achieved when the system temperature is between 21 °C (70 °F) and 35 °C (95 °F). When used in the pigment grind, it is not sensitive to high temperatures and no minimum temperature is required.

NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.

© Copyright 2006, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

LEVELS OF USE

In the variety of systems where BENTONE SD-1 can be used, use levels are typically 0.2 % - 2.0 % by weight of the system, with the level dependent upon the degree of thickening, sag and pigment settling control desired.

When evaluating BENTONE SD-1 additive as a replacement for conventional organoclays, a good starting point is a level equal to that of BENTONE 34 additive.

Because BENTONE SD-1 additive is effective in systems, rather than in solvents alone, it is not suitable for lubricating greases and similar binderless products.

HANDLING AND SAFETY

More detailed information on handling and safety for each product is included in the relevant material safety data sheet, available for each product.

STORAGE RECOMMENDATIONS

Store in a cool, dry location.

PACKAGING

BENTONE SD-1 rheological additive is available in multi-ply paper bags. Please contact your local Elementis Specialties representative for the packaging available in your region.

SHELF LIFE

BENTONE SD-1 has a shelf life of 4 (four) years from date of manufacture.

PRODUCT NUMBER

10799

QUALITY ASSURANCE

Since 1992 the company is a holder of the ISO 9001 / ISO 9002 certificates, which guarantees that all operations are conducted according to the stipulated standards.

USA Head Office

Elementis Specialties, Inc.
P.O. Box 700
329 Wyckoffs Mill Road
Hightstown, NJ 08520 USA
Tel.: +1 609 443 2500
Fax: +1 609 443 2422

Europe

Elementis Service Centre NV
De Kleetlaan 12A, P.O. Box 3
1931 Diegem, Belgium
Tel.: +32 2 790 76 00
Fax: +32 2 790 76 60

Asia

Elementis Specialties, Inc.
120 Jalan Kapar 27/89
40400 Shah Alam
Malaysia
Tel.: +60 3 5192 2887
Fax: +60 3 5192 3887

Japan

Elementis Japan KK
15-14 Minaminisemba 1-Chome
Chou-Ku, Osaka
542-0081 Japan
Tel.: +81 6 6267 6211
Fax: +81 6 6267 6215