

Pigment Dispersing Agent

GENERAL INFORMATION

NUOSPERSE® FA 196 is a highly concentrated liquid pigment dispersing agent for application in organic solvent-borne systems. NUOSPERSE® FA 196 is especially recommended for application as a dispersing agent for carbon black, for thermoplastic acrylic systems and as an auxiliary product to improve the action of universal tinting pastes in basic alkyd paints.

PHYSICAL PROPERTIES

Appearance 20 °C : clear liquid
 Active content : 100 %
 pH, 1 % solution in water
 (ASTM D 1172) : 5.0 – 6.0
 Density, 20 °C
 (ISO 2811-2) : approx. 1040 kg/m³
 Viscosity, 25 °C
 (ASTM D 2196) : max. 1200 mPa.s
 Colour, 25% solution in water
 (DIN-EN 1557) : max. 150 Alpha
 Solubility : soluble in water and most organic solvents
 Composition : surface active compound
 Ionic character : anionic

APPLICATION AND PROPERTIES

NUOSPERSE® FA 196 is applicable in practically all organic solvent-borne paint and ink systems e.g., oxidatively drying systems, and thermoplastic systems.

Feature

- Strong adsorption on a wide range of pigment surfaces

Consequence

- improved colour development
- better and faster dispersion
- reduced rub-up and colour float
- improved compatibility of universal colorants
- absorbs onto a wide variety of pigments
- enables the replacement of several more specific dispersants with just one product

- Multi-functional Character

- 100% active matter

- solvent-free
- highest effectiveness

- As a dispersing agent for carbon black: An addition of ca. 1 % of NUOSPERSE® FA 196, calculated on the total quantity of the milling paste improves the colouring power and counteracts flocculation of various types of carbon black. NUOSPERSE® FA 196 must be added before the dispersing process.

- As a pigment dispersing agent in thermoplastic acrylic systems and in non-aqueous dispersions: In both of the above mentioned systems, NUOSPERSE® FA 196 gives the following advantages:
 - Higher gloss
 - Better colouring power
 - Better and quicker dispersion

The product must be applied at a dosage of ca. 1.0 % calculated on the milling paste, before the dispersing process.

(continued)

NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.

© Copyright 2009, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

® Trademark of Elementis Specialties, Inc.

- As an auxiliary product to improve the performance of universal tinting pastes in standard alkyd paint:

NUOSPERSE® FA 196 forms a bridge between the alkyd paint and the universal tinting paste, which results in better flow, colouring power, gloss and stability.

The required dosage of NUOSPERSE® FA 196 is 0.2 – 0.4 % calculated on the total quantity of alkyd paint.

- As a wetting agent in paint removers and brush cleaners:

NUOSPERSE® FA 196 improves the penetration of the paint remover into the paint layer and of the brush cleaner into the brush. We recommend a dosage of 2 – 6 % calculated on the total amount of the paint remover or brush cleaner.

- As a wetting agent in universal pigment dispersions:

Pigment dispersions based on NUOSPERSE® FA 196 in combination with NUOSPERSE® FN 265 are used for the shading of various coatings, such as dispersion paints and alkyd paints etc. Normally up to 10% of the pigment slurry may be added to the coating.

- As a wetting / dispersing agent in solvent based inks:

Pigment dispersions based on NUOSPERSE® FA 196 provide the following advantages:

- Better pigment wetting;
- Better colour strength;
- Better flow.

HEALTH AND SAFETY DATA

Before using this product please consult our Material Safety Data Sheet (MSDS) for information on safe handling and storage. MSDS's can be found on the company website at www.elementis-specialties.com.

SHELF LIFE

NUOSPERSE® FA 196 has a shelf life of 3 (three) years from date of manufacture.

QUALITY ASSURANCE

Since 1992 the company is a holder of the ISO 9001 / ISO 9002 certificates, which guarantees that all operations are conducted according to the stipulated standards.

USA Head Office

Elementis Specialties, Inc.
P.O. Box 700
329 Wyckoffs Mill Road
Hightstown, NJ 08520 USA
Tel.: +1 609 443 2500
Fax: +1 609 443 2422

Europe

Elementis Service Centre NV
De Kleetlaan 12A, P.O. Box 3
1931 Diegem, Belgium
Tel.: +32 2 790 76 00
Fax: +32 2 790 76 60

Asia

Elementis Specialties, Inc.
120 Jalan Kapar 27/89
40400 Shah Alam
Malaysia
Tel.: +60 3 5192 2887
Fax: +60 3 5192 3887

Japan

Elementis Japan KK
15-14 Minaminisemba 1-Chome
Chou-Ku, Osaka
542-0081 Japan
Tel.: +81 6 6267 6211
Fax: +81 6 6267 6215