

## Wetting and Dispersing Agent

### GENERAL INFORMATION

NUOSPERSE® FX 9360 is suitable for solvent-based coatings. It provides good wetting and dispersing performance to organic pigments and carbon blacks.

### PHYSICAL PROPERTIES

Composition	highly branched copolymer containing multiple anchoring groups
Appearance	yellow to brown liquid
Non-volatile content	38 - 42 %
Solvent	n-butyl acetate
Specific gravity	ca. 0.98 g/cm <sup>3</sup>

### APPLICATIONS

- Suitable for most organic pigments and carbon blacks
- Recommended for various coating systems such as industrial coatings and automotive coatings

### KEY PROPERTIES

- It deflocculates pigments and prevents re-flocculation through steric hindrance.
- To reduce grinding time and mill base viscosity.
- To improve color development, hiding power, gloss and evenness.

### INCORPORATION

Incorporated before grinding, dispersing with pigment to achieve optimum effect.

### LEVELS OF USE

- Recommended dosage
  - Organic pigments: 20 - 40 %
  - Carbon blacks: 50 -150 %
- Due to the variation of surface and oil-absorption characteristics of pigments as well as compatibility of dispersing agent in each system, it is suggested to test at various dosages on pigment to obtain optimum results.

### HANDLING AND SAFETY

- As it contains a solvent, the product requires special care in handling.
- Avoid any eye and skin contact.
- For further information please check to SDS. MSDS can be found on the company website at [www.elementis-specialties-asia.com](http://www.elementis-specialties-asia.com).

### STORAGE RECOMMENDATIONS

- Keep away from sources of ignition and heat.
- Keep container tightly closed in a dry and well-ventilated place.
- Stored between 0 °C to 40 °C.

### PACKAGING

Net Weight: 25 kg

*NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.*

*© Copyright 2006, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.*

*® Trademark of Elementis Specialties, Inc.*

[www.elementis-specialties-asia.com](http://www.elementis-specialties-asia.com)

B03 Jul-15

## **SHELF LIFE**

NUOSPERSE® FX 9360 has a shelf life of 24 months from date of manufacture.

## **QUALITY ASSURANCE**

Since 1992 the company is a holder of the ISO 9001 / ISO 9002 certificates, which guarantees that all operations are conducted according to the stipulated standards.

---

### **Elementis Specialties**

#### **Asia Head Office China**

**Deuchem (Shanghai) Chemical Co., Ltd.**  
99, Lianyang Road,  
Songjiang Industrial Zone,  
Shanghai, China 201613  
Tel.: +86 21 57740348  
Fax.: +86 21 57743563

#### **Taiwan**

**Deuchem Co., Ltd.**  
92, Kuang-Fu North Road,  
Hsinchu Industrial Park,  
Hukou, Hsinchu, Taiwan  
Tel.: +886 3 5984035  
Fax.: +886 3 5983301

#### **Malaysia**

**Elementis S.E.A. (Malaysia) Sdn. Bhd.**  
**(1095769-X)**  
62-1, Jalan Tasik Utama 5,  
Medan Niaga Tasik Damai,  
Sungai Besi, 57000 Kuala Lumpur, Wilayah  
Persekutuan, Malaysia  
Tel.: +603-9054 6690  
Fax.: +603-9054 6698

#### **India**

**Elementis Specialties (India) Pvt. Ltd.**  
Unit B, Ground Floor,  
Jaswanti Landmark,  
Mehra Industrial Estate,  
L.B.S Marg, Vikhroli (West),  
Mumbai 400 079, India  
Tel.: + 91 22 67421251  
Fax.: + 91 22 67421252