

Highly Efficient Nonionic Synthetic Associative Thickener (NiSAT) for High Shear-Rate Viscosity Build in Water-Borne Systems

GENERAL INFORMATION

RHEOLATE[®] HX 6008 is a 25% active high-shear (ICI) nonionic synthetic associative thickener (NiSAT) for aqueous applications. It develops high shear viscosity very efficiently with some mid-shear viscosity contribution in the newer VOC-free acrylic and styrene/acrylic latex systems, without sacrificing flow and leveling.

RHEOLATE[®] HX 6008 is APEO, VOC, and tin-free. It is designed for use in latex paints and other waterborne systems where maintaining viscosity at high shear during product application and improved film leveling are required. The product is a pourable and pumpable liquid.

RHEOLATE[®] HX 6008 can be used alone in small particle size latex systems or in combination with a co-thickener such as RHEOLATE[®] 655 if more mid-shear viscosity is required.

PHYSICAL PROPERTIES

Composition	polyether polyurethane resin solution in water
Appearance	Opaque Liquid
Active non-volatile content (% by weight)	25
Carrier Solvent	100% water
Specific Gravity	1.05
Viscosity (cps)	1,000 – 4,000
pH	4 – 6
VOC (ASTM D 6886-03)	<0.01%

APPLICATIONS

- High quality, low VOC latex paints, particularly based on acrylic technology

KEY PROPERTIES

- Very high efficiency
- Low tendency to syneresis
- Compatible in all resin systems and especially efficient with acrylic and styrene acrylic resins
- Excellent balance of sag and leveling
- Outstanding flow and leveling
- Superior spatter resistance
- Zero VOC
- Easy to use

INCORPORATION

RHEOLATE[®] HX 6008 can be used as supplied or, if necessary, further diluted with water. Addition can take place at any time during the manufacturing process but incorporation into the mill base before letdown is recommended. RHEOLATE[®] HX 6008 additive can be combined with other associative rheological additives, clay based thickeners or cellulosic thickeners for higher package viscosity.

RHEOLATE[®] HX 6008 is an associative rheological additive and is generally more efficient as the particle size of the latex decreases. It is important to assess the effectiveness of RHEOLATE[®] HX 6008 in the complete system, as performance is also affected by other raw material ingredients. Details of the associative nature of nonionic synthetic associative thickeners can be found in the Elementis Specialties RHEOLOGY HANDBOOK.

LEVELS OF USE

Typical use levels of RHEOLATE[®] HX 6008 are 0.5% to 3.0% (thickener solids weight) on total system weight.

NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.

© Copyright 2014, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

® Trademark of Elementis Specialties, Inc.

www.elementis-specialties.com

v 1.0 March 2014

REGULATORY

For the most current regulatory status, please refer to the MSDS for RHEOLATE[®] HX 6008

HEALTH AND SAFETY DATA

Detailed information on handling and safety could be found in the material safety data sheet. Handle in accordance with good industrial hygiene and safety practices. Avoid contact with skin, eyes and clothing. Avoid breathing mists, dusts, or vapours. Wash hands thoroughly after handling.

STORAGE RECOMMENDATIONS

RHEOLATE[®] HX 6008 should be kept above 4°C (40°F). In the event of accidental freezing, thaw gently, spread a portion between glass slides and examine for granules. If found, do not use.

PACKAGING

Available in pails, drums and IBC packaging. Please contact your local Elementis Specialties representative for the packaging available in your region.

SHELF LIFE

RHEOLATE[®] HX 6008 has a shelf life of 24 months from date of manufacture.

QUALITY ASSURANCE

Since 1992 the company is a holder of the ISO 9001 / ISO 9002 certificates, which guarantees that all operations are conducted according to the stipulated standards.

USA Head Office

Elementis Specialties, Inc.
469 Old Trenton Road
East Windsor, NJ 08512
USA
Tel.: +1 609 443 2500
Fax: +1 609 443 2422

Europe

Elementis UK Ltd
c/o Elementis GmbH
Stolberger Strasse 370
50933 Cologne
Germany
Tel.: +49 221 2923 2066
Fax: +49 221 2923 2011

China

Deuchem (Shanghai) Chemical Co., Ltd.
99, Lianyang Road
Songjiang Industrial Zone
Shanghai
China 201613
Tel.: +86 21 5774 0348
Fax: +86 21 5774 3563